

APLAX PP ENGINEERING PLASTICS

Properties	UNIT	Test Method	Aplax P1017GN 02
Mechanical			
抗張強度 Tensile Str, Yield	psi	D-638	3000
斷裂伸長率 Tensile Elongation, Break	%	D-638	30
彎曲強度 Flexural Strength	psi	D-790A	6200
彎曲彈性率 Flexural Modulus	psi	D-790A	400000
IZOD衝擊強度 Izod Impact Strength, Notched	ft-lb/in 23°C -30°C	D-256	0.7
硬度 Rockwell Hardness	R-Scale	D-785	95
Thermal			
融點 Melting Point	°C	D-789	165
熱變形溫度 Heat Deflection Temperature	°C 66 psi 264 psi	D-648	132
線膨脹係數 Coefficient of Thermal Expansion	E-5 1/°C	D-696	-
熾熱電線耐燃試驗 Glow Wire Test	°C	IEC 695-2-1	-
Electrical			
介電強度 Dielectric Strength	kv/mm	D-149	-
體積電阻 Volume Resistivity	ohm-cm	D-257	-
耐電弧 Arc Resistance	sec	D495	-
Other			
比重 Specific Gravity	-	D-792	1.4
成型收縮率 Mold Shrinkage · Flow	% 3mm	D-955	1.3
吸水率 Water Absorption	% 23°C, 24hr	D-570	0.03
Flammability			
燃燒性 Flammability	1/8" 1/16" 1/32"	UL-94	HB HB HB
附註 Remark	Unreinforced PP 50% Mineral reinforde		

*Typical properties can be subject to change without further notice.

ISO9001 / ISO14001 / IECQ HSPM ASSURANCE

GINAR
Marketing Communications Department TAIWAN
Phone +886-3-3868820 Fax +886-3-3863587 www.ginar.com.tw
Http: // www.ginar.com.tw
E-mail: ginar@ ginar.com.tw

單位換算	抗張強度, 彎曲強度, 彎曲彈性率	IZOD 衝擊強度
	1psi=0.0703 kg/cm ²	1 ft-lb/in =5.45 kg-cm/cm
	1Mpa=10.2 kg/cm ²	1J/m=0.102 kg-cm/cm